

Product Data Sheet

PHOEPSOX® 3314 LG

1/2

Maj 2021



Phoepox® 3314 LG

is a high performance fusion bonded epoxy powder that is designed as both a stand-alone layer or as the first layer in a dual layer FBE anti corrosion pipe coating system. Phoepox® 3314 LG possesses enhanced corrosion protection properties. Phoepox® 3314 LG is suitable for standard service temperatures. Phoepox® 3314 LG can also be used as a primer in multi-layer polyolefin systems.

			Typical Value	Test Method / Device
POWDER PROPERTIES	GEL TIME	at 200°C	33-48 seconds	ISO 8130-6
	THERMAL PROPERTY	Tg1	60 ± 5°C	ISO 21809-2
		Tg2	101 ± 5°C	
		ΔH	40-80 J/g	
	DENSITY		1.5 ± 0.1 g/cm ³	Gas Pycnometer
	PARTICLE SIZE		99.8% < 250 μm	Laser Scattering
	MOISTURE CONTENT		≤ 0.5%	CSA Z245.20-14
COLOR		Grey		
PHYSICAL TESTS	CATHODIC DISBONDING *	1-3 mm at -3.5 VDC, 65°C, 24 hours 2-4 mm at -1.5 VDC, 20°C, 28 days 3-4 mm at -1.5 VDC, 65°C, 28 days		CSA Z245.20-14
	ADHESION *	Rating 1 at 75°C, 24 hours		CSA Z245.20-14
	FLEXIBILITY *	Pass, at 3°, -30°C		CSA Z245.20-14
	WATER RESISTANCE	No blistering at 38°C, 15 weeks No blistering at 90°C, 5 weeks		ASTM D870



◀ **Engineered Materials** for a Modern World.

Product Data Sheet

PHOEPOX® 3314 LG

2/2



STORAGE STABILITY 12 months from production date in $\leq 23^{\circ}\text{C}$ and $\leq 65\%$ relative humidity. Cooler temperatures and lower humidity are recommended.

* The performance will be affected by surface preparation and curing condition.

APPLICATION DATA

SURFACE PREPARATION	Surface must be free from contamination
SURFACE ROUGHNESS	50-100 μm
RECOMMENDED FILM THICKNESS	200-400 μm
APPLICATION TEMPERATURE	215-240 $^{\circ}\text{C}$
TIME TO QUENCH	≥ 90 sec at 225 $^{\circ}\text{C}$ metal temperature