

PHOENIX 2K FastSeal

Product Data Sheet

Rev. 1 - July 2006



Product Description

PHOENIX 2K FastSeal is a cold-applied, reaction-curing polyurethane bitumen product consisting of PHOENIX 2K FastSeal, Components A and B mixed in a volume ratio of 1:1 in specially designed mixing and application equipment, PHOENIX Pumps.

This product is specially developed to seal asphalt and concrete joints against penetration by water, frost, chemical and fuel spills.

PHOENIX 2K FastSeal is specially formulated to adhere to the substrates of asphalt and concrete while remaining stable but flexible.

Delivery

All products are delivered in 10 or 20 litre cans or packed customized for specific purposes.

Application

Before application both components must be stirred separately.

Component A and B are then mixed in the specially designed PHOENIX Pump in a 1:1 volume ratio. Application speed varies from 2 to 7 litres per minute depending on the specific task and choice of PHOENIX Pump.

Equipment

There are various PHOENIX Pumps for product application and the choice of equipment depends on the project in question.

The pump is either leased or bought, and operator training is part of the service provided by PHOENIX INTERNATIONAL A/S.

Cleaning

Cleaning of the PHOENIX Pump equipment is very easy. Simply discard the nozzle before application - making the system easy to use.

Storage

The cans must be stored out of direct sunlight and at a maximum temperature of 30°C. The shelf life is two years from date of delivery.

Standards

PHOENIX 2K Resin has been tested and approved in accordance with ISO EN IEC 840.

Quality Control

Quality control is carried out at the PHOENIX INTERNATIONAL A/S laboratory. All products are tested and test certificates are issued on request.

The logo consists of a red triangle pointing to the left, followed by the text 'corrosion protection that stays.' in a bold, black, sans-serif font.

Technical Data

| Property | Unit | Unit | Methods |
|--|--------------------|--|--------------------|
| Density | g/ml | 1.01 | PHOENIX 11.00.012 |
| Colour | - | Black | - |
| Fire class | - | none | |
| Cleaning | - | Oil remover, water and soap, mechanical removal | - |
| Potlife | min. | approx. 10 | PHOENIX 9.00.002 |
| Hardness, 24 h | Shore A | approx. 30 | DIN 53505 (6.87) |
| Hardness, cured | Shore A | approx. 60 | DIN 53505 (6.87) |
| Curing time | hr | approx. 48 | - |
| Exotherm | °C | approx.60 | volume 120 L |
| Tensile strength | N/mm ² | approx 3.0 | DIN 53455 (8.81) |
| Elongation | % | approx. 300 | DIN 53455 (8.81) |
| Water absorption 50°C, 56 days | % | 0.91 | PHOENIX 9.00.001 |
| Fuel resistance, change in mass isooctane/toluene diesel | % | +3.9 +2.3 | SS-S-200- (8.88) |
| Chemical resistance: (change in weight) Air Water, neutral Water, pH10 Water, pH>13 | % | - 0.25 0.0 - 0.25 - 0.25 | - |
| Corrosion test, 1000 h Saltwater fog | - | No change with a coating of 20-25 mm. After exposure the steel looks exactly like before | ASTM B 177-73 |
| Hydrolysis resistance: Tensile strength Elongation Shore A | % of initial value | approx. 84 approx. 88 approx. 94 | VDE 0291, Teil2-97 |
| UV-resistance, 1000 h | - | The compound turns slightly grey and some erosion <1mm may appear in the surface | ASTM G-53-93 |
| Heat transferability | mW/m*K | approx. 153.5 | DIN 52 612-79 |
| Dielectric strength | kV/mm | >20 | ASTM D 149-93a |
| Volume resistivity ½ min. dry 1 min. dry 5 min. dry | Ohm x cm | 1.2 x 10 ¹⁴ 1.5 x 10 ¹⁴ 2.1 x 10 ¹⁴ 2.1 x 10 ¹⁴ | ASTM D 257-93 |
| Application temperature | °C | Between 5 - 30 | ASTM B 177-73 |